CPP FilmsProduct Portfolio





About the IPAK Group

Headquartered in Karachi, IPAK was founded in 2017 as a green field project to manufacture "BOPP" packaging films. The company's state-of-the-art manufacturing facility is spanning over an area of ~7 acres land, where the major machinery has been acquired from the world's top class engineering firms such as Bruckner Maschinenbau (Germany), BOBST (United Kingdom), KAMPF (Germany), etc.

IPAK is a budding yet high growth potential company with a focus to develop and deliver excellent quality packaging films to the local as well as international markets.

Staying committed to its unwavering strategic objectives, the company decided to expand its business footprint, by incorporating three new subsidiaries which will enable the group to become the only flexible packaging group of Pakistan, offering a one-window solution for all four kinds of commonly used packaging films known as BOPP, BOPET, CPP and Metallized.





FAST GROWING FILMS MANUFACTURER IN PAKISTAN



PIONEER
OF 5-LAYERS
FILM IN
PAKISTAN



Product Portfolio

Transparent Films

Range includes films with high transparency and gloss, low SIT, wide seal range, modified slip and primarily used for printing and lamination.

► Metallized Films

It is used for single and two-ply packaging structure and lamination application in chips/snacks packaging.


White Films

Due to high gloss, milky white appearance and better stiffness, these films are highly demanded for Biscuit, Confectionery, Chocolate and Ice Cream packaging.

Transparent Films

CTH21 | Previous CTHo

Properties	Units	Values			
Thickness	μ	20.00	25.00	30.00	40.00
Grammage	gm/m²	18.20	22.75	27.30	36.40
Yield	m²/kg	54.95	43.95	36.60	27.45
Density	g/cm³	0.91			



DCTN01

Properties	Units	Values
Thickness	μ	15.00
Grammage	gm/m²	13.65
Yield	m²/kg	73.25
Density	g/cm³	0.91










Metallized Films


CMZ10S | Previous CMZ

Properties	Units	Values				
Thickness	μ	15.00	18.00	20.00	25.00	30.00
Grammage	gm/m²	13.65	16.38	18.20	22.75	27.30
Yield	m²/kg	73.25	61.05	54.95	43.95	36.60
Density	g/cm³	0.91				
WVTR	gm/m²/24hrs	0.60				
OTR	cc/m²/24hrs	80.00				




CMZ10R | Previous CMZ-HB

Properties	Units	Values			
Thickness	μ	20.00	25.00	30.00	
Grammage	gm/m²	18.20	18.20	27.30	
Yield	m²/kg	54.95	43.95	36.60	
Density	g/cm³	0.91			
WVTR	gm/m²/24hrs	0.30			
OTR	cc/m²/24hrs	30.00			



CMZW10 | Previous CMZ-WS

Properties	Units	Values		
Thickness	μ	30.00	40.00	
Grammage	gm/m²	28.50	38.00	
Yield	m²/kg	35.00	26.30	
Density	g/cm³	0.95		
WVTR	gm/m²/24hrs	0.70		
OTR	cc/m²/24hrs	90.00		












White Films

CW21 | Previous CWSo

Properties	Units	Values		
Thickness	μ	15.00	20.00	25.00
Grammage	gm/m²	14.25	19.00	23.75
Yield	m²/kg	70.20	52.60	42.10
Density	g/cm³		0.95	










Our Subsidiaries













(7) (⊚) (in) ⊗